

Application Number 10/598095
Response to the Office Action dated 12/28/2007

RECEIVED
CENTRAL FAX CENTER

MAR 27 2008

Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in this application.

Listing of Claims:

1. (Currently Amended) A method for producing a compound single crystal comprising:

growing a compound single crystal by reacting a source gas with a material solution including other materials,

wherein the source gas includes at least one of nitrogen and ammonia, and the other materials include at least one Group III element selected from the group consisting of gallium, aluminum, and indium and a flux material, and

wherein a template that comprises a semiconductor layer expressed as a composition formula $Al_uGa_vIn_{1-u-v}N$ ($0 \leq u \leq 1$, $0 \leq v \leq 1$, and $0 \leq u + v \leq 1$) is placed in the material solution beforehand, and

wherein a Group III nitride single crystal is grown while stirring the material solution to create a flow from a gas-liquid interface in contact with the source gas toward an inside of the material solution.

2. (Original) The method according to claim 1, using a single crystal production apparatus comprising a heating unit and a closed pressure- and heat-resistant container that is heated inside the heating unit,

wherein the source gas of the compound single crystal and other materials are provided to the container and sealed in a pressurized atmosphere,

the container is housed in the heating unit,

a material solution is prepared by heating the container in the heating unit so that the other materials melt into a liquid, and

Application Number 10/598095
Response to the Office Action dated 12/28/2007

under these conditions, a single crystal is grown by reacting the source gas with the material solution while the material solution is stirred.

3. (Original) The method according to claim 2, wherein the single crystal is grown by reacting the source gas with the material solution while the material solution is stirred by rocking the container.

4. (Original) The method according to claim 3, wherein the container is rocked by rocking the heating unit.

5. (Original) The method according to claim 2, wherein a crucible is set in the container, and at least one of an inside and an inner wall of the crucible has at least one selected from the group consisting of (A) impeller, (B) baffle, (C) template, and (D) helical protrusions.

6. (Original) The method according to claim 3, wherein the rocking is at least one selected from the group consisting of a shift motion, a linear repetitive motion, a pendular motion, a rotational motion, and a combined motion of any of these motions.

7. (Original) The method according to claim 2, wherein the other materials include a flux material.

8. (Original) The method according to claim 3, wherein the single crystal production apparatus further comprises a source gas supply unit,

the source gas supply unit is connected to the container in which the other materials have been put, supplies the source gas to the container, and is separated from the container after supplying the source gas, and subsequently the container is rocked.

Application Number 10/598095
Response to the Office Action dated 12/28/2007

9. (Original) The method according to claim 8, wherein the source gas supply unit is separated from the container after heating the container so that the other materials melt into a liquid and adjusting a pressure in the container.
10. (Original) The method according to claim 2, wherein a pressure of the source gas in the container is reduced after formation of the single crystal.
11. (Original) The method according to claim 2, wherein the single crystal production apparatus further comprises an auxiliary tank system for supplying the source gas, and the auxiliary tank system is connected to the container.
12. (Original) The method according to claim 3, wherein the single crystal production apparatus further comprises a source gas supply unit, the source gas supply unit and the container are connected by a flexible pipe, and the container is rocked without being separated from the source gas supply unit.
13. (Canceled)
14. (Original) The method according to claim 1, wherein the flux material includes at least one of an alkali metal and alkaline-earth metal.
15. (Currently Amended) The method according to claim 2, wherein ~~a~~the template that comprises a semiconductor layer expressed as a composition formula:
 $\text{Al}_u\text{Ga}_v\text{In}_{1-u-v}\text{N}$ ($0 \leq u \leq 1$, $0 \leq v \leq 1$, and $0 \leq u + v \leq 1$) is placed in the container beforehand.
16. (Original) The method according to claim 15, wherein the material solution is prepared by heating in the container, the source gas is dissolved in the material solution, and subsequently the template is immersed in the material solution.

Application Number 10/598095
Response to the Office Action dated 12/28/2007

17. (Original) The method according to claim 15, wherein a crucible is set in the container, and the template is a sheet template and placed substantially upright on a bottom of the crucible.
18. (Original) The method according to claim 17, wherein the container is rocked so that the material solution moves parallel to the sheet template.
19. (Original) The method according to claim 7, wherein at least the flux material is removed from the container after the growth of the compound single crystal is finished.
20. (Original) The method according to claim 19, wherein the material solution includes at least gallium and sodium, and a heating temperature of the material solution is 100°C (373 K) or more.
21. (Original) The method according to claim 20, wherein the heating temperature is 300°C (573 K) or more.
22. (Original) The method according to claim 20, wherein the heating temperature is 500°C (773 K) or more.
23. (Original) The method according to claim 1, wherein a growth rate of the Group III nitride single crystal is 30 $\mu\text{m}/\text{hour}$ or more.
24. (Original) The method according to claim 1, wherein a growth rate of the Group III nitride single crystal is 50 $\mu\text{m}/\text{hour}$ or more.
25. (Original) The method according to claim 1, wherein a growth rate of the Group III nitride single crystal is 100 $\mu\text{m}/\text{hour}$ or more.

Application Number 10/598095
Response to the Office Action dated 12/28/2007

26. (Original) The method according to claim 2, wherein a pressure of the source gas in the container is 5 atm ($5 \times 1.01325 \times 10^5$ Pa) to 1000 atm ($1000 \times 1.01325 \times 10^5$ Pa).

27. (Original) The method according to claim 2, wherein the heating unit is filled with an inert gas.

28. (Original) The method according to claim 2, wherein when the other materials include gallium, the following formula (1) is satisfied:

$$V \times (P/1.01325 \times 10^5) \times (T1/T) > (X/2a) \times 22.4 \times 2 \quad (1)$$

where X (g) is a weight of gallium to be consumed, a (= 69.723) is an atomic weight of gallium, V (liter) is an internal volume of the container, P (Pa) is an ambient pressure during a growth process (formation of the single crystal), T (K) is a growth temperature, and T1 (K) is a temperature at which the other materials are weighed.

29. (Original) The method according to claim 28, wherein the following formula (2) is satisfied instead of the formula (1):

$$V \times (P/1.01325 \times 10^5) \times (T1/T) > (X/2a) \times 22.4 \times 5 \quad (2).$$

30. (Original) The method according to claim 28, wherein the following formula (3) is satisfied instead of the formula (1):

$$V \times (P/1.01325 \times 10^5) \times (T1/T) > (X/2a) \times 22.4 \times 10 \quad (3).$$

31. (Original) The method according to claim 2, wherein the single crystal production apparatus comprises a pipe for connecting the container in the heating unit and the outside of the heating unit, and the pipe has a structure that is likely to prevent aggregation of at least one of the material solution and the other materials.

32. (Original) The method according to claim 31, wherein an inner diameter of the pipe is 3 mm or less.

Application Number 10/598095
Response to the Office Action dated 12/28/2007

33. (Original) The method according to claim 31, wherein an inner diameter of the pipe is 2 mm or less.

34. (Canceled)

35. (Canceled)

36. (Canceled)

37. (Canceled)

38. (Canceled)

39. (Canceled)

40. (Canceled)

41. (Canceled)

42. (Canceled)